



# NEAR EDGE WAX RESIN

## Technical Specifications

Color Code Tab .....	Copper
Maximum Print Speed .....	24 IPS
Film Thickness .....	4.5
Microns	
Total Ribbon Thickness .....	7.6
Microns	
Transmission Density .....	1.10
	MacBeth
	Scale
Ink Melting Point .....	
	70°C/158°F

## Near Edge Wax/Resin

### Fast Processing

#### Benefits

- Specially developed for near edge printers
- Produces exceptionally black bar codes and images with no show through
- Broad stock latitude, prints well on both rough, uncoated stocks and smooth, coated stocks
- Mid-range scratch and smear resistance
- Print speeds up to 24 IPS in flexible packaging

#### Recommended Stock

Coated and Uncoated	Polypropylene
Polyolefin (i.e. Tyvek)	Polyethylene
Paper Tag & Label Stocks	



What you need to know to quote ribbon business.

**Thermal Transfer Ribbon STORAGE CONDITIONS**  
 For optimal print results, thermal transfer printing should occur in the temperature range of 41° F to 95° F at 45% to 85% relative humidity. Suggested storage conditions for up to one year duration are 23° F to 104° F at 20% to 85% relative humidity. Exposing thermal transfer ribbons to direct sunlight or moisture will cause damage to the ribbons.



Ph: (800) 700-7377  
 Ph: (949) 888-3880  
 Fax: (949) 888-3883

**ACCURATE IMAGING RESOURCES**  
 22532 Avenida Empresa  
 Rancho Santa Margarita, CA 92688